

MEDITE TRICOYA EXTREME (MTX) USAGE GUIDELINES – WINDOWS, DOORS AND ANCILLARIES

MEDITE TRICOYA EXTREME (MTX) panels exhibit outstanding durability and dimensional stability. The added benefits of light weight, moisture stable, sustainable raw materials and extended guarantees offer endless opportunities for external use.

This information sheet offers best practice guidelines for enhanced service life and care for external use of MTX.



CONSTRUCTION RECOMMENDATIONS

- All edges should be rounded to 3mm radius to improve paint retention and maximise maintenance intervals
- Flat surfaces/areas where water can collect should be avoided. Surfaces should have 15° inclination to allow water to naturally run off
- All gaps/holes should be sealed to prevent water entering the construction
- Fixings and fasteners must be stainless steel of A2 or A4 (EN 10088-1) quality or AISI type 304 or 316
- If the coating is damaged during installation the necessary repairs should be performed in line with the coating manufacturers guidelines
- D4 class or equivalent adhesives must be used

COATING RECOMMENDATIONS

- MTX does not need a coating to maintain its durability and dimensional stability. Any coating applied to MTX should be of a high quality and to the coating manufacturers specification

- As MTX is a wood-based panel it can absorb low levels of water. Moisture will not negatively impact board properties
- MTX moisture content should be below 10% before processing and coating application
- All edges and machined surfaces should be effectively sealed to help prevent moisture ingress
- High moisture ingress can negatively impact the durability and appearance of coatings
- Coating specifications and guidelines set out by the coating manufacturer must be followed e.g. surface preparation, wet film thickness and drying techniques
- All surfaces and edges should be coated with the same system and number of coats
- The coating system should be fully finished prior to installation. On site coating should be avoided as it can lead to incorrect film thickness, exposure to moisture and an unbalanced coating system
- Customers should review the location of a site to determine if it would classify as high risk for surface biological growth and would necessitate a biocide additive in the coating formulation

MAINTENANCE RECOMMENDATIONS

All coating systems will require regular maintenance and eventual recoating. Coating systems applied to MTX will have an increased lifespan due to the board's unique properties. Please see our website for warranted coating systems.

Moulds and algae growths can occur on any timber or wood-based panels. Their presence is related to temperature, humidity, wetting and the presence of atmospheric mould spores.

Moulds and algae may grow on the surface of painted MTX. The mould will not decay the board or affect its durability.

- 1) Inspect all joinery at least once a year
- 2) Repair any small areas of coating damage as soon as possible
- 3) Wash surfaces with a solution of warm water and liquid detergent, ensuring the water is changed frequently
- 4) Rinse thoroughly with clean water
- 5) Use deionised water for best results
- 6) The build-up of dirt on joinery surfaces can encourage mould growth
- 7) Check joinery for signs of algae or mould growth
- 8) Treat affected areas with a solution of one-part household bleach to two-parts water
- 9) Allow 20 minutes to act and wash off with cold water and a stiff nylon brush
- 10) Use deionised water for best results
- 11) Recoat when there are general signs of wear

It is recommended that customers contact the coating manufacturer for expertise and guidance.



CONTACT MEDITE SMARTPLY FOR
TECHNICAL SUPPORT FOR MEDITE
TRICOYA EXTREME (MTX)

www.mdfosb.com +44 (0) 1322 424900



The mark of
responsible forestry

MEDITE® is a registered trademark of MEDITE EUROPE DAC ("MEDITE") and cannot be used or reproduced without MEDITE's written permission. Tricoya®, Accoya® and the trimarque device are registered trademarks owned by Accsys Technologies, the trading name of Titan Wood Ltd.